

This document is confidential and is proprietary to the American Chemical Society and its authors. Do not copy or disclose without written permission. If you have received this item in error, notify the sender and delete all copies.

**Evolution of Graphene Molecules: Structural and Functional Complexity  
as Driving Force behind Nanoscience**

Journal:	<i>ACS Nano</i>
Manuscript ID:	nn-2014-03283d
Manuscript Type:	Perspective
Date Submitted by the Author:	17-Jun-2014
Complete List of Authors:	Müllen, Klaus; Max-Planck-Institute for Polymer Research,

SCHOLARONE™  
Manuscripts


## Evolution of Graphene Molecules: Structural and Functional Complexity as Driving Forces behind Nanoscience

Klaus Müllen

Max-Planck-Institute for Polymer Research


Mainz, Germany

**Abstract:** The evolution of nanoscience is based on the ability of the fields of chemistry and physics to share competencies through mutually beneficial collaborations. With this in mind, in this Perspective, I describe three classes of compounds: rylene dyes, polyphenylene dendrimers, as well as nanographene molecules and graphene nanoribbons, which have provided a superb platform to nurture these relationships. The synthesis of these complex structures is demanding, but also rewarding because they stimulate unique investigations at the single-molecule level by scanning tunneling microscopy and single-molecule spectroscopy. There are close functional and structural relationships between the molecules chosen. In particular, rylene and nanographenes can be regarded as honeycomb-type, discoid species composed of fused benzene rings. The benzene ring can thus be regarded as a universal modular building block. Polyphenylene dendrimers serve, first, as a scaffold for dyes *en route* to multichromophoric systems and, second, as chemical precursors for graphene synthesis. Through chemical design, it is possible to tune the properties of these systems at the single-molecule level and to achieve nanoscale control over their self-assembly to form multifunctional (nano)materials.



Chemistry is an essential part of nanoscience because it involves the materials, either molecules or particles, that make up the field, while also introducing an artistic element through eloquent synthetic design. Because nanoscience focuses on nano-sized objects and their assemblies, it is imperative to acknowledge the need to visualize and to manipulate the individual molecular building blocks by physical methods such as scanning tunneling microscopy (STM) and single-molecule spectroscopy (SMS). Herein, I describe how synthetic chemistry and these physical characterization techniques have formed a beneficial, yet mutually challenging collaboration aimed at advancing nanoscience.<sup>1</sup>

However, more sophisticated characterization by these methods demands structurally perfect and increasingly complex, multifunctional molecules. For example, areas like electronics and optoelectronics require conjugated molecules with extended  $\pi$ -systems,<sup>2-5</sup> which represent an enormous playground for the synthesis of both small organic molecules and polymers. The unique features of these structures, such as the ability to take up and to transport electrons or to interact with light and to undergo excitation energy transfer, is what qualifies them as active components of devices. By examining the field of nanoscience, one can conclude that the synthesis of new complex molecules has spurred new physical experiments capable of characterizing them, and, in turn, these new physical techniques have encouraged the pursuit of even more complicated syntheses. Therefore, I wish to demonstrate the advantages of the fruitful interplay between physics and chemistry for three classes of conjugated molecules: rylene-type chromophores (Scheme 1); shape-persistent dendrimers made from twisted, tightly packed interlocked benzene rings; and graphene molecules and related graphene nanoribbons (GNRs, Scheme 1).



**Scheme 1:** Rylenes (**1**), graphene molecules (**2**) (**3**) and graphene nanoribbons (**4**)

1  
2  
3 These examples of conjugated species were chosen based on a few obvious  
4 characteristics.

5  
6 Chromophores, while representing a seemingly mature field of chemistry, are still in  
7 high demand from both an industrial and a fundamental point of view. One reason for  
8 this undiminished need for these materials is that chromophores can serve not only  
9 as colorants, but also as semiconductors, sensors, and biological probes.<sup>6</sup> In regard  
10 to single-molecule properties, the workhorse of the SMS community has been the red  
11 terrylene dye (TDI, **1b**). However, more complex studies have required  
12 chromophores with a broad variation of absorption and emission wavelengths and,  
13 even more important, ultrahigh photostability.<sup>7</sup>

14  
15  
16  
17 Control over functional groups such as redox centers, catalysts, or receptors requires  
18 their perfect nano-site definition. This has prompted the synthesis of dendrimers as  
19 scaffolds for the design of “unimolecular” functional nanoparticles.<sup>8</sup> Our  
20 polyphenylene dendrimers have provided such structures due to their shape  
21 persistence, which guarantees geometrically defined placement of the functional  
22 units in their nanoenvironments.


23  
24  
25  
26 There has been a tremendous amount of effort spent on the fabrication of graphene  
27 and its derivatives through chemical and physical methods with varying levels of  
28 sophistication.<sup>9</sup> Currently, graphenes are predominately obtained by top-down  
29 methods (*i.e.*, exfoliation from graphite),<sup>10</sup> but these methods yield products that lack  
30 structural perfection, especially when employing graphene oxide as an intermediate.  
31 Hence, it is necessary to utilize synthetic, bottom-up methods to achieve graphene  
32 materials with control over their chemical and physical structures.<sup>11–13</sup>

33  
34  
35  
36 Herein, the benzene ring serves as a modular building block in proceeding from small  
37 organic molecules to extended oligomers and finally their related polymers. Next to  
38 the size of the chemical structure, the second most important design principle is their  
39 dimensionality. Linear (one-dimensional [1D]) poly-para-phenylenes are the prototype  
40 of conjugated polymers, with their two-dimensional (2D) analogues being graphene  
41 molecules, which we regard as 2D polymers. Remarkably enough, we synthesize  
42 them from dendritic three-dimensional (3D) polyphenylenes. It is this evolution of  
43 chemical synthesis that we define as a true bottom-up protocol.

44  
45  
46  
47 Interdisciplinary efforts appear to be a key ingredient of nanoscience, since it is too  
48 difficult for a single research group to possess the necessary combination of  
49 chemical and physical expertise. Finding the right partners, however, can be another  
50 obstacle. Fortunately, with our collaborators, we have found a successful balance  
51 between achievements in chemistry and physics while still challenging one another  
52 toward even more difficult shared goals. I will mention these collaborations in the  
53 appropriate sections to highlight their accomplishments, and, additionally, I would like  
54 to dedicate this article to each and every one of them.

## Rylene Chromophores

Perylene tetracarboxydiimide (PDI, **1a**) has been known for nearly a century and it has found extensive commercial use, while also serving as the workhorse of many electronic and optoelectronic investigations. A bulk heterojunction solar cell fabricated from a PDI as the electron acceptor and a hexabenzocoronene (HBC, **2b**) derivative as the electron donor has paved the way toward nanophase separation in solar cells with the formation of separate percolation pathways of holes and electrons.<sup>14</sup> The photovoltaic activity in electron acceptor/electron donor blends based on nanoscale phase segregated PDI architectures and poly-3-hexyl-thiophene (P3HT) has been monitored for the first time at the nanoscale by Kelvin probe force microscopy (KPFM), in collaboration with Paolo Samori.<sup>15</sup> The build-up of a homologous series of rylene dyes (Figure 1) has enabled a systematic variation of absorption and emission wavelengths reaching far into the near infrared. Since the new opportunities for device fabrication have been extensively described elsewhere,<sup>8</sup> here, I focus on the role of these chromophores as stimuli for nanoscience.




**Figure 1:** Homologous series of rylene dyes (**1a–1e**).

As expected, increases in the ribbon size up to 4 nm in length required the substitution of alkyl chains at the imide, as well as the ring positions to achieve soluble materials. Physisorption from solution and visualization of HDI (**1e**) by STM in the group of Steven De Feyter revealed the concentration-dependent formation of multilayers. Application of shear forces resulted in large-area alignment of these multilayers at the organic liquid–solid interface. Quinonediiimine (QDI, **1c**) was found to form two different patterns of 2D crystals, the relative abundance of which could also be controlled by shear flow.<sup>7,16</sup>

As to optical detection, Christoph Bräuchle and Thomas Basché have shown terrylene diimide (TDI, **1b**) to be an ideal chromophore for SMS due to its high

1  
2  
3 fluorescence quantum yield and its emission above 700 nm, which made it applicable  
4 as a tracking molecule for biological studies.<sup>7,17–19</sup> The main advantage of TDI (**1b**)  
5 and its analogues over other dyes, some of which may be commercially available, is  
6 their extremely high photostability. This property also proved to be advantageous for  
7 the case of dibenzo-fused QDI, which has a bathochromically shifted emission  
8 spectrum.<sup>20,21</sup> Here, SMS work by Nick van Hulst aimed to achieve coherent control  
9 and manipulation of vibrational wave-packet interference at room temperature, and  
10 these remarkable experiments required unprecedented stability of a chromophore  
11 made by design.  
12  
13  
14



43  
44 **Scheme 2:** Different multichromophoric systems.

45  
46 The next logical step was to characterize multichromophores by SMS techniques  
47 (Scheme 2). Dyad **5** was synthesized with a PDI donor and TDI acceptor that were  
48 covalently connected by a rigid oligophenylene spacer, which was used to control the  
49 distance and dipole orientation factor between the units. Single-molecule  
50 spectroscopy provided unique insights into energy transfer mechanisms at the single-  
51 molecule level, as well as to the limits of description by the Förster model.<sup>22</sup> This  
52 process was further extended toward the modulation of energy transfer between  
53 individual molecules or the application of external stimuli, for example, by mechanical  
54 forces. Thus, together with the group of Thomas Basché, we made and studied  
55 multichromophore **6** in which a central TDI unit was surrounded by four perylene  
56 dicarboxy monoimide (PMI) dyes.<sup>23</sup> This complex system was deposited on a surface  
57  
58  
59  
60


1  
2  
3 and subjected to compressive stress exerted by the tip of an atomic force  
4 microscope. Conformational changes of the multichromophore occurred, leading to  
5 changes in the electronic states, which in turn were monitored by SMS. We could  
6 thereby detect spectral shifts that were reversible, as well as those that persisted,  
7 even after removal of the tip. A future challenge would be to incorporate structural  
8 functionalities that are capable of undergoing *cis-trans* isomerization (see below) into  
9 such chromophores synthetically, and to investigate the impact of this type of  
10 transformation at the molecular level by SMS.  
11  
12

13  
14 Similarly complex in terms of synthesis and of photophysics, but equally rewarding  
15 from a nanoscience point of view, were the cases of molecules **7** and **7a**.<sup>24</sup> These  
16 materials were designed with the goal of resembling molecular machines. A perylene  
17 or terrylene dicarboximide moiety was attached to a tetraphenylmethane core  
18 yielding a tripod with three ammonium functional groups for anchoring onto a  
19 substrate surface. The dye was oriented either along the main C<sub>3</sub> axis of the system  
20 or possessed a twist due to the presence of a meta-phenylene unit. The rotation of  
21 the dye around the central axis within the actual molecular rotor was monitored by  
22 defocused wide-field imaging in the group of Johan Hofkens. Here, it was a critical  
23 issue to bias the Brownian motion and to control the speed of the rotation, where one  
24 significant factor was the viscosity of the surrounding solvent. Another important  
25 factor, which was more difficult to understand, was the polarization of the excitation  
26 light field, because it would not be realistic to assume a sufficient optical torque.  
27 Rather, it was necessary to invoke a fluctuating friction model in this case. Thereby,  
28 the transition dipole tended to adopt the same direction as the optical field vector  
29 since this was when the probability for an excitation event was highest.  
30  
31  
32  
33  
34

### 35 **Dendritic Multichromophores**

36  
37 From there, we deemed it straightforward to proceed to more complex  
38 multichromophores by incorporating multiple dye molecules to investigate degenerate  
39 or directional energy transfer. In this case, it was necessary to achieve perfect spatial  
40 definition of the chromophores, and toward that end, we could involve a different  
41 object of our nanochemistry, the polyphenylene dendrimers.<sup>9</sup> Scheme 3 illustrates  
42 their structures (**9–11**), which indeed represent a unique class amongst the  
43 dendrimer field because they i) are only made from twisted, tightly packed benzene  
44 rings, ii) can be obtained with structural perfection and monodispersity up to  
45 molecular weights above 1.5 MDa thanks to the use of repetitive Diels-Alder  
46 cycloaddition reactions,<sup>25</sup> iii) possess outstanding chemical stability, and iv) are  
47 shape-persistent due to the lack of back-bending of the dendron arms. The semi-rigid  
48 character of these structures is a remarkable aspect that guarantees the perfect site  
49 definition of active groups such as chromophores, redox centers, or catalysts, and it  
50 is this feature that discriminates the polyphenylene macromolecules from other  
51 dendrimers.  
52  
53  
54  
55  
56  
57  
58  
59  
60





**Scheme 3:** Different polyphenylene dendrimers (only lower generation showed).

A special case was dendrimer **8**, which possessed naphthalene dicarboxy monoimide antennae on the rim, PDI units throughout the scaffold, and a central TDI molecule as the core.<sup>26</sup> This system generated a unique light-harvesting complex in which excitation energy transfer onto the core could occur in a direct or stepwise fashion, and this process was studied by Frans De Schryver and Johan Hofkens *via* SMS. Many other light-induced processes could also be analyzed through these functional 3D-macromolecules, such as electron transfer between different incorporated molecules or the isomerization of azobenzene units. The latter case is particularly appealing from a nanoscientific point of view since multiple azobenzene “hinges” placed in an otherwise rigid dendrimer scaffold (**10**) yielded spherical macromolecules whose size could be changed upon exposure to light.<sup>27</sup> Furthermore, a unique aspect of these “breathing” dendrimers was that through the *trans-cis* isomerization of the azobenzenes the macromolecules could stably encapsulate guest species, which were only released upon opening the dendritic cages by the *cis-trans* transformation.

Thus, polyphenylene dendrimers create a unique functional nanoenvironment by way of a perfect covalent design. While these materials provide numerous opportunities that are appealing to nanoscience, they extend beyond the scope of the present article. However, I would be remiss not to mention some of the future challenges in the field: i) it has been shown that the inner voids of these dendrimers can be tuned to act as perfect receptors for explosives, and, in conjunction with an ultramicrobalance, they can be used as sensors with picomolar detection limits.<sup>28</sup> It is important to utilize such host–guest interactions for other gas-sensing purposes; ii)




1  
2  
3 borate functional groups can be encapsulated within the dendrimer core (**11**) to  
4 achieve weakly coordinating anions (WCAs).<sup>29</sup> These macromolecular ions hold  
5 great promise for controlling chemical reactions, for example, in stabilizing cationic  
6 zirconocenium catalysts during polyolefin synthesis. On the physicochemical side,  
7 the dendritic shell can be used to separate spatially anionic and cationic species  
8 approaching the Bjerrum length of the ion pair.<sup>30</sup>  
9  
10

11 These dendrimers constructed from branched and densely packed benzene rings  
12 exhibit yet another feature that qualifies them as a key constituent of synthetically  
13 driven nanoscience: they serve as a molecular carbon source for transformation into  
14 2D graphene molecules. The exciting potential of such a 3D to 2D interconversion is  
15 that it lays the groundwork for bottom-up synthesis of graphenes, and, more  
16 importantly, the connectivity of the dendrimer precursors defines the size and  
17 periphery of the graphenic products.  
18  
19  
20

### 21 **Graphene Molecules and Graphene Nanoribbons**

22  
23 Polycyclic aromatic hydrocarbons (PAHs), as pioneered by Erich Clar, have played a  
24 crucial role in the advancement of organic chemistry.<sup>31,32</sup> In 1995, we started a  
25 program toward obtaining larger and larger PAHs, with our “superbenzene”  
26 hexabenzocoronene (HBC, **2**) as the most visible case.<sup>33</sup> The synthesis included the  
27 planarization of the hexaphenylbenzene precursor **2'** (Scheme 4). Furthermore, it  
28 was necessary to attach soft alkyl substituents to the parent HBC to make it solution  
29 processable. This enabled visualization by STM not only based upon vacuum  
30 deposition, but also upon physisorption on substrates such as highly oriented  
31 pyrolytic graphite (HOPG) from solution. Remarkably elegant STM experiments at the  
32 solid–liquid interface were then performed by Jürgen Rabe and Paolo Samori.<sup>1,34</sup>  
33 Subsequent chemical developments have included i) increasing the size of the discs,  
34 often by designing homologous series; ii) varying the periphery from arm-chair to zig-  
35 zag patterns; and iii) incorporating heteroatoms or forming ionic derivatives. In all  
36 cases, the synthesis proceeded *via* cyclodehydrogenation (flattening) of suitably  
37 designed polyphenylene precursors.<sup>35,36</sup> Indeed, the precursor of nanographene **3**  
38 (C222) is compound **3'**, which turned out to be nothing more than a first-generation  
39 polyphenylene dendrimer with a hexaphenylbenzene core. In every case, the  
40 synergy between synthesis and STM studies proved to be of outstanding value.  
41 Additionally, STM was accompanied by scanning tunneling spectroscopy (STS) to  
42 gather information on the electronic structure of the surface-immobilized PAHs and to  
43 compare this information with the outcome of other spectroscopic  
44 characterization.<sup>37,38</sup>  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60




**Scheme 4:** From non-planar polyphenylene precursors to disc-type graphene molecules.

At this time, we would like to point out two more synthetic achievements that were particularly important from a nanoscience perspective. First, perfect edge chlorination of the discs induced ring puckering, and thus provided sufficient solubility for single crystal growth and structural analysis.<sup>39</sup> These graphene molecules can be synthesized with diameters up to 4 nm, and while this may be rather large from an organic chemistry stand point, they still possess structural perfection and are solution processable. It is possible to increase the size of these molecules even further; these materials will be outlined below for the case of graphene nanoribbons (GNRs).

Second, more complex PAH derivatives were made, such as the dyad **2c** in which a HBC unit was connected to anthraquinone.<sup>40</sup> After STM visualization, a donor molecule was placed from solution on top of the anthraquinone acceptor, thus creating a new dipole next to the HBC. The resulting electrical field could act as a gate for the tunneling current through the HBC and therefore afford a model case for a single-molecule field-effect transistor (FET). In other studies, HBC could be functionalized with two thiol anchor groups and then subjected to break junction-STM measurements of the electrical conduction.<sup>41</sup> Molecular wires have been a long-lasting query of nanoscience and a comparison of 1D and 2D species is among the key topics.

There is, admittedly, an appreciable gap between nanometer-sized, molecularly defined graphenes<sup>42</sup> and the micron-sized graphene flakes made by top-down methods. Before we start to close this gap synthetically, let us take a brief look at the

high charge carrier mobility for graphene,<sup>43,44</sup> which would qualify graphene as a useful semiconductor in a high-modulation FET.<sup>45</sup> However, this is hampered by the vanishing band gap of graphene, which excludes a proper off-behavior and limits the general use of graphene in digital electronics. Yet it is possible to open the band gap through geometric confinement, which has been demonstrated through the production of GNRs.<sup>46</sup> With this in mind, various approaches toward the fabrication of GNRs have been taken, such as lithography of graphene precursors or unzipping of carbon nanotubes.<sup>14,47</sup> The obvious disadvantage of such protocols is the lack of structural definition of the edges and this defines a pressing need for a bottom-up synthesis method.




**Scheme 5:** Synthesis of graphene nanoribbons in solution.

It might be mentioned that as early as 1993 we synthesized polymer **12**<sup>48</sup> as part of our work toward double-stranded polyphenylenes, and **12a** is indeed a GNR (Scheme 5). Since 2010, we have introduced a whole new class of GNRs with polymer **4a** as the most recent example<sup>49</sup> (Scheme 5). The synthesis included the twisted precursor polymer **13a** which was obtained by a repetitive Diels-Alder cycloaddition of the AB-type monomer **13**. The polymer was then, as described above, subjected to intramolecular dehydrogenation, yielding GNR **4a**. The planarized macromolecule, due to its extensive alkyl substitution, was still solution processable, and after fractionation, it could be obtained with a length of 600 nm. Visualization and proof of the structural perfection were achieved by the group of Steven De Feyter *via* STM after deposition onto graphite or a gold surface. Current-potential curves were measured by Chongwu Zhou after the GNRs were deposited from solution between electrodes, and the resulting devices could even be used for gas sensing.<sup>50</sup> Since the fabrication of FETs with organic semiconductors<sup>11,51</sup> is often obstructed by large contact resistances it was important that the charge carrier mobilities could also be detected in a contact-free mode by terahertz spectroscopy in the group of Mischa Bonn.<sup>52</sup>


Some key challenges for synthesis of future chemical GNRs are: i) to further increase their size while also varying the aspect ratios, and control the edge structures; ii) to

incorporate heteroatoms; iii) to form block copolymers from GNR blocks with different widths and thus different bandgaps; and iv) to end-cap with functional groups toward anchoring at electrodes. Needless to say, all of these structural changes are essential for future device studies, but require sophisticated chemical expertise.



**Scheme 6:** Synthesis of tribenzocoronene **14a** by electrocyclic ring closure from cyclophane **14**.

These syntheses, while enabling rewarding nanoscience, will push the limits of classical polymer chemistry. However, there is one problem: the decreasing solubility of larger and larger ribbons. While the use of soft-landing in collaboration with Paolo Samori<sup>53</sup> was shown to be a method to process larger and larger PAHs into ordered crystalline monolayers on a conductive substrate, such a deposition method is extremely slow. In this framework, a key breakthrough in view of processing limitations was pioneered by the group of Roman Fasel through an atomically precise GNR synthesis. Their protocol comprised UHV-deposition of small building blocks onto metal surfaces and monitoring of the whole process by STM. Our organic model reaction was the transformation of cyclophane **14** into the PAH **14a** (Scheme 6). This stepwise electrocyclic ring closure could be accomplished by photolysis in solution, but also by heating the precursor on a Cu(111) surface with STM control.<sup>54</sup> Related work in the literature<sup>55,56</sup> made use of dibromo derivatives of aromatic building blocks that were immobilized on metal surfaces. Thermal carbon–halogen bond cleavage furnished intermediate diradicals that could still diffuse on the surface and polymerize to form conjugated polymer chains. In a similar fashion, we could achieve the polymerization of the dibromobianthryl building block **15a** in spite of the prevailing steric hindrance. However, the formation of GNR **15** required subsequent flattening of the precursor polymer, and this became possible in a further heating step (Figure 2).<sup>57</sup> Then, it was logical to apply a surface-bound monolayer synthesis to other polymer topologies such as chevron structures,<sup>57</sup> which could simply be realized by the choice of the dibromo monomer. Furthermore, polymer networks became accessible by introducing tribromo-substituted building blocks. Along these lines, we could accomplish the synthesis of 2D layers with atomically precise pores for possible use as membranes.<sup>58</sup>




**Figure 2:** Schematic illustration for the surface-assisted synthesis of  $N = 7$  GNR **15**. a) Vacuum deposition of 10,10'-dibromo-9,9'-bianthryl monomer **15a** on a metal surface. b) Debromination of **15a** to form surface-stabilized biradical intermediates. c) Radical polymerization to form covalent bonds between the monomer units. d) Preplanarization upon thermal activation, followed by e) surface-assisted cyclodehydrogenation to give GNR **15**.

Chemical reactions on surfaces and, in particular, GNR synthesis under the control of STM and STS have become a very active new field of nanoscience.<sup>59-61</sup> Many questions remain to be answered though, such as, i) the occurrence of side reactions or the coupling of neighboring ribbons, ii) the mechanism of polymer growth upon diffusion of intermediate oligomers, and iii) the feasibility of reactions other than aryl-aryl coupling.<sup>62,63</sup> However, there are remarkable opportunities that mainly follow from the choice of the monomeric starting compound and that help to tailor the electronic structure of the product. This can be achieved, as with solution synthesis, *via* doping of the resulting GNR by incorporation of heteroatoms into the monomer or by varying the width and edges of the ribbon. Particularly exciting will be GNRs with zig-zag peripheries because they promise unique edge states, and thus offer an entry into spintronics. Another problem is the need to execute this synthesis from metal substrates. The latter enables STM control and might lead to the stabilization of reactive intermediates. Furthermore, they offer additional opportunities by preorganization of monomers or polymers on the surface or by combining different building blocks in a programmable fashion. However, conducting surfaces exclude charge transport measurements, and subsequent device fabrication would require transfer to insulating surfaces by lift-off techniques.



From a physical point of view, we have looked at the characterization of graphene molecules by STM and SMS side by side since they both provide significant breakthroughs in single-molecule detection. Apart from the physical methods, there is also a structural connection between our families of graphene and rylene molecules. Indeed, rylene dyes represent a special topology of PAHs in which the HOMO-LUMO gaps are particularly small. Rylenees can also be regarded as a narrow GNR, and this relation could be further corroborated by a chemical reaction, the Hunsdiecker decarboxylation.<sup>64</sup> Thereby, PDIs were transformed into tetrabromo perylenes **16** (Scheme 7). These compounds were used by Lifeng Chi and Harald Fuchs as unique building blocks for GNR **16a** formation on gold surfaces. The same GNRs could also be achieved when starting from a tetrabromonaphthalene **17**. A key aspect of both protocols is that ribbon formation does not require a cyclodehydrogenation step. It is mechanistically remarkable that the fusion of two naphthalene units *via* their peri-positions proceeds by an aurate complex **17a** in which the four peri-positions are connected by two gold centers.



**Scheme 7:** On-surface synthesis of rylene-type graphene nanoribbons.

Therefore, it is a unique feature of our GNR fabrication, both in solution and on surfaces, that their geometric and electronic structures can be tuned by the nature of the monomeric building blocks. Some chemical challenges have been outlined already but many more can be envisaged, such as the inclusion of monodisperse oligomers as model compounds or selective reactions at the edges to tune the band



1  
2  
3 gaps further. More physical methods would have to be employed, such as Raman  
4 spectroscopy and X-ray photoelectron spectroscopy, to complement these  
5 syntheses.  
6

## 7 **Conclusion and Prospects**

8  
9  
10 The present cases were chosen to document the cross-fertilization between design  
11 and synthesis on one hand and single-molecule detection on the other. These  
12 selected examples should provide evidence that nanoscience must go beyond the  
13 catalogue of commercial compounds to make use of our collective chemical  
14 imagination. The toolbox of synthetic methods must be combined with overarching  
15 design concepts, where the size and dimensionality of molecules is of particular  
16 interest. The resulting bottom-up approach of materials synthesis offers the  
17 advantages of structural perfection and reproducibility.  
18  
19

20  
21 While many further challenges have already been outlined, there remain no limits for  
22 the multidisciplinary interactions discussed herein. The beauty of materials synthesis  
23 cannot be further exemplified, although the many obstacles of extremely intricate  
24 syntheses have not been expounded on in this Perspective. It becomes obvious,  
25 however, that all these structural and functional modifications immediately create  
26 opportunities for fresh nanoscience, both in bulk and at the single-molecule level.  
27 While the emphasis of this Perspective has been on fundamental aspects, there is  
28 also room for applications of which a few cases shall be mentioned: rylenes can be  
29 used as near-infrared absorbers in heat management; surface-functionalized  
30 dendrimers act as drug-delivery vehicles capable of crossing the blood–brain barrier;  
31 detection of lung cancer from breath analysis requires chemiresistors based upon  
32 graphene molecules and carbon nanotubes; 1,2-diketone functionalities at the edge  
33 of graphenes establish catalytic activity in the dehydrogenation of ethylbenzene to  
34 styrene; structurally perfect graphene molecules hold special promise as  
35 semiconductors for FETs; and there is so much more to come.  
36  
37  
38  
39  
40

## 41 **Acknowledgments**

42  
43 The author acknowledges, next to the many partner groups, the dedicated work of  
44 many associates. Without their skill and creativity this Perspective would not have  
45 been possible. Also acknowledged is financial support by the EU projects FP7-  
46 Energy-2010-FET Project Molesol (FP7-Energy-2010 256617), EU Project GENIUS  
47 (ITN-264694) Superior (ITN-238177), and the Integrated projects RADSAS (NMP3-  
48 CT-2004-001561), ONE-P (NMP3-LA-2008-212311), and NAIMO (NMP4-CT-2004-  
49 500355). Of particular importance is the ERC-Adv.-Grant 267160 (NANOGRAPH).  
50 Additional financial support was provided by Volkswagen Foundation, Max-Planck-  
51 Society (ENERCHEM), Federal Ministry of Education and Research (BMBF)  
52 (Projects LiBZ and Graphenoid-Lagen), and the German Science Foundation (DFG)  
53 within the frame of the ESF Projects GOSPEL (09-EuroGRAPHENE-FP-001),  
54 SONS2-SUPRAMATES, DFG Priority Programs SPP 1355, SPP 1459, and the  
55  
56  
57  
58  
59  
60

collaborative research project SFB 625. Industrial collaborations with BASF AG, Ludwigshafen were also essential to the success of this work.

## References

- 1 Samori, P.; Rabe, J. P. Scanning Probe Microscopy Explorations on Conjugated (Macro)molecular Architectures for Molecular Electronics. *J. Phys. Condens. Mater* **2002**, *14*, 9955–9973.
- 2 Chua, L. L.; Zaumseil, J.; Chang, J. F.; Ou, E. C. W.; Ho, P. K. H.; Sirringhaus, H.; Friend, R. H. General Observation of *n*-Type Field-Effect Behaviour in Organic Semiconductors. *Nature* **2005**, *434*, 194–199.
- 3 Brédas, J. L.; Silbey, R. *Conjugated Polymers*. Kluwer Academic Publishers, The Netherlands **1991**.
- 4 Henson, Z. B.; Müllen, K.; Bazan, G. C. Seeking Design Strategies for Organic Semiconductors beyond the Molecular Formula, *Nat. Chem.* **2012**, *4*, 699–704.
- 5 Diez-Perez, I.; Hihath, J.; Hines, T.; Wang, Z. S.; Zhou, G.; Müllen, K.; Tao, N. J. Controlling Single-Molecule Conductance Through Lateral Coupling of  $\pi$  Orbitals. *Nat. Nanotechnol.* **2011**, *6*, 226–231.
- 6 Chen, L.; Li, C.; Müllen, K. Beyond Perylene Diimides: Synthesis, Assembly and Function of Higher Rylene Chromophores. *J. Mater. Chem. C* **2014**, *2*, 1938–1956.
- 7 Weil, T.; Vosch, T.; Hofkens, J.; Peneva, K.; Müllen, K. The Rylene Colorant Family-Tailored Nanoemitters for Photonics Research and Applications. *Angew. Chem. Int. Ed.* **2010**, *49*, 9068–9093.
- 8 Türp, D.; Nguyen, T. T. T.; Baumgarten, M.; Müllen, K. Uniquely Versatile: Nano-Site Defined Materials Based on Polyphenylene Dendrimers. *New J. Chem.* **2012**, *36*, 282–298.
- 9 Geim, A. Graphene: Status and Prospects, *Science* **2009**, *324*, 1530–1534.
- 10 Li, X.; Wang, X.; Zhang, L.; Lee, S.; Dai, H. Chemically Derived, Ultrasoft Graphene Nanoribbon Semiconductors. *Science* **2008**, *319*, 1229–1232.
- 11 Dreyer, D. R.; Ruoff, R. S.; Bielawski, C. W. From Conception to Realization: An Historical Account of Graphene and Some Perspectives for Its Future. *Angew. Chem. Int. Ed.* **2010**, *49*, 9336–9344.
- 12 Zhu, Y. W.; Murali, S.; Cai, W. W.; Li, X. S.; Suk, J. W.; Potts, J. R.; Ruoff, R. S. Graphene and Graphene Oxide: Synthesis, Properties, and Applications. *Adv. Mater.* **2010**, *22*, 5226–5226.
- 13 Chen, L.; Hernandez, Y.; Feng, X. L.; Müllen, K. From Nanographene and Graphene Nanoribbons to Graphene Sheets: Chemical Synthesis. *Angew. Chem. Int. Ed.* **2012**, *51*, 7640–7654.
- 14 Schmidt-Mende, L.; Fechtenkötter, A.; Müllen, K.; Moons, E.; Friend, R. H.; MacKenzie, J. D. Self-Organized Discotic Liquid Crystals for High-Efficiency Organic Photovoltaics. *Science* **2001**, *293*, 1119–1122.
- 15 Liscio, A.; Palermo, V.; Fenwick, O.; Braun, S.; Müllen, K.; Fahlman, M.; Cacialli, F.; Samori, P. Local Surface Potential of  $\pi$ -Conjugated Nanostructures by Kelvin Probe Force Microscopy: Effect of the Sampling Depth. *Small* **2011**, *7*, 634–639.
- 16 Yuan, Z.; Lee, S.-L.; Chen, L.; Li, C.; Mali, K. S.; De Feyter, S.; Müllen, K. Processable Rylene Diimide Dyes up to 4 nm in Length: Synthesis and STM Visualization. *Chem. Eur. J.* **2013**, *19*, 11842–11846.

- 1  
2  
3 17 Jung, C.; Ruthardt, N.; Lewis, R.; Michaelis, J.; Sodeik, B.; Nolde, F.; Peneva, K.;  
4 Müllen, K.; Bräuchle, C. Photophysics of New Water-Soluble Terrylenediimide  
5 Derivatives and Applications in Biology, *Chem. Phys. Chem.* **2009**, *10*, 180–190.  
6 18 Mais, S.; Tittel, J.; Basché, T.; Bräuchle, C.; Gohde, W.; Fuchs, H.; Müller, G.;  
7 Müllen, K. K Terrylenediimide: A Novel Fluorophore for Single-Molecule  
8 Spectroscopy and Microscopy from 1.4 K to Room Temperature. *J. Phys. Chem.*  
9 *A* **1997**, *101*, 8435–8440.  
10 19 Herrmann, A.; Müllen, K. From Industrial Colorants to Single Photon Sources and  
11 Biolabels: The Fascination and Function of Rylene Dyes. *Chem. Lett.* **2006**, *35*,  
12 978–985.  
13 20 Kinkhabwala, A.; Yu, Z. F.; Fan, S. H.; Avlasevich, Y.; Müllen, K. Moerner, W. E.  
14 Large Single-Molecule Fluorescence Enhancements Produced by a Bowtie  
15 Nanoantenna. *Nat. Photonics* **2009**, *3*, 654–657.  
16 21 Brinks, D.; Stefani, F. D.; Kulzer, F.; Hildner, R.; Taminiau, T. H.; Avlasevich, Y.;  
17 Müllen, K.; Van Hulst, N. F. Visualizing and Controlling Vibrational Wave Packets  
18 of Single Molecules. *Nature* **2010**, *465*, 905–908.  
19 22 Kim, H. N.; Puhl, L.; Nolde, F.; Li, C.; Chen, L.; Basché, T.; Müllen, K. Energy  
20 Transfer at the Single-Molecule Level: Synthesis of a Donor-Acceptor Dyad from  
21 Perylene and Terrylene Diimides, *Chem. Eur. J.* **2013**, *19*, 9160–9166.  
22 23 Stottinger, S.; Hinze, G.; Diezemann, G.; Oesterling, I.; Müllen, K.; Basché, T.  
23 Impact of Local Compressive Stress on the Optical Transitions of Single Organic  
24 Dye Molecules. *Nat. Nanotechnol.* **2014**, *9*, 182–186.  
25 24 Hutchison, J. A.; Uji-i, H.; Deres, A.; Vosch, T.; Rocha, S.; Müller, S.; Bastian, A.  
26 A.; Enderlein, J.; Nourouzi, H.; Li, C.; *et al.* A Surface-Bound Molecule that  
27 Undergoes Optically Biased Brownian Rotation. *Nat. Nanotechnol.* **2014**, *9*, 131–  
28 136.  
29 25 Räder, H. J.; Nguyen, T. T.T.; Müllen, K. MALDI-TOF Mass Spectrometry of  
30 Polyphenylene Dendrimers up to the Megadalton Range. Elucidating Structural  
31 Integrity of Macromolecules at Unrivalled High Molecular Weights.  
32 *Macromolecules* **2014**, *47*, 1240–1248.  
33 26 Cotlet, M.; Vosch, T.; Habuchi, S.; Weil, T.; Müllen, K.; Hofkens, J.; De Schryver,  
34 F. Probing Intramolecular Forster Resonance Energy Transfer in a  
35 Naphthaleneimide-Peryleneimide-Terrylenediimide-Based Dendrimer by  
36 Ensemble and Single-Molecule Fluorescence Spectroscopy. *J. Am. Chem. Soc.*  
37 **2005**, *127*, 9760–9768.  
38 27 Nguyen, T. T. T.; Türp, D.; Wang, D. P.; Nölscher, B.; Laquai, F.; Müllen, K. A  
39 Fluorescent, Shape-Persistent Dendritic Host with Photoswitchable Guest  
40 Encapsulation and Intramolecular Energy Transfer. *J. Am. Chem. Soc.* **2011**,  
41 *133*, 11194–11204.  
42 28 Lubczyk, D.; Grill, M.; Baumgarten, M.; Waldvogel, S. R.; Müllen, K. Scaffold-  
43 Optimized Dendrimers for the Detection of the Triacetone Triperoxide Explosive  
44 Using Quartz Crystal Microbalances. *Chem. Plus. Chem.* **2012**, *77*, 102–105.  
45 29 Nguyen, T. T. T.; Türp, D.; Wagner, M.; Müllen, K. Photoswitchable Conductivity  
46 in a Rigidly Dendronized Salt. *Angew. Chem. Int. Ed.* **2013**, *52*, 669–673.  
47 30 Moritz, R.; Zardalidis, G.; Butt, H.-J.; Wagner, M.; Müllen, K.; Floudas, G. Ion  
48 Size Approaching the Bjerrum Length in Solvents of Low Polarity by Dendritic  
49 Encapsulation. *Macromolecules* **2014**, *47*, 191–196.  
50 31 Clar, E. *Polycyclic Hydrocarbons*. Academic Press. London, **1964**.  
51 32 Clar, E. *The Aromatic Sextet*. Wiley. London, **1972**.  
52 33 Stabel, A.; Herwig, P.; Müllen, K.; Rabe, J. P. Diode-Like Current-Voltage Curves  
53 for a Single Molecule- Tunneling Spectroscopy with Submolecular Resolution of  
54  
55  
56  
57  
58  
59  
60

- 1  
2  
3 an Alkylated, Pericondensed Hexabenzocoronene. *Angew. Chem. Int. Ed.* **1995**,  
4 *34*, 1609–1611.
- 5 34 Samori, P. Scanning Probe Microscopies Beyond Imaging. *J. Mater. Chem.*  
6 **2004**, *14*, 1353–1366.
- 7 35 Watson, M. D.; Fechtenkötter, A.; Müllen, K. Big is Beautiful – 'Aromaticity'  
8 Revisited from the Viewpoint of Macromolecular and Supramolecular Benzene  
9 Chemistry. *Chem. Rev.* **2001**, *101*, 1267–1300.
- 10 36 Müllen, K. Graphene as a Target for Polymer synthesis. *Adv. Polym. Sci.* **2013**,  
11 *262*, 61–92.
- 12 37 Mali, K. S.; Adisoejoso, J.; Ghijsens, E.; De Cat, I.; De Feyter, S. Exploring the  
13 Complexity of Supramolecular Interactions for Patterning at the Liquid–Solid  
14 Interface. *Acc. Chem. Res.* **2012**, *45*, 1309–1320.
- 15 38 De Feyter, S.; De Schryver, F. C. Self-Assembly at the Liquid/Solid Interface:  
16 STM Reveals. *J. Phys. Chem. B* **2005**, *109*, 4290–4302.
- 17 39 Tan, Y. Z.; Yang, B.; Parvez, K.; Narita, A.; Osella, S.; Beljonne, D.; Feng, X. L.;  
18 Müllen, K. Atomically Precise Edge Chlorination of Nanographenes and its  
19 Application in Graphene Nanoribbons. *Nat. Commun.* **2013**, *4*, 2646.
- 20 40 Müllen, K.; Rabe, J. P. Nanographenes as Active Components of Single-  
21 Molecule Electronics and How a Scanning Tunneling Microscope Puts Them To  
22 Work. *Acc. Chem. Res.* **2008**, *41*, 511–520.
- 23 41 Diez-Perez, I.; Li, Z.; Hihath, J.; Li, J.; Zhang, C.; Yang, X.; Zang, L.; Dai, Y.;  
24 Feng, X. L.; Müllen, K.; *et al.* Gate-Controlled Electron Transport in Coronenes as  
25 a Bottom-Up Approach towards Graphene Transistors. *Nat. Commun.* **2010**, *1*,  
26 *31*.
- 27 42 Feng, X.; Marcon, V.; Pisula, W.; Hansen, M. R.; Kirkpatrick, J.; Grozema, F.;  
28 Andrienko, D.; Kremer, K.; Müllen, K. Towards High Charge-Carrier Mobilities by  
29 Rational Design of the Shape and Periphery of Discotics. *Nat. Mater.* **2009**, *8*,  
30 *421–426*.
- 31 43 Britnell, L.; Gorbachev, R. V.; Geim, A. K.; Ponomarenko, L. A. Resonant  
32 Tunnelling and Negative Differential Conductance in Graphene Transistors. *Nat.*  
33 *Commun.* **2013**, *4*, 1794.
- 34 44 Pisula, W.; Feng, X. L.; Müllen, K. Charge-Carrier Transporting Graphene-Type  
35 Molecules. *Chem. Mater.* **2011**, *23*, 554–567.
- 36 45 Chen, D.; Tang, L.; Li, J. Graphene-Based Materials in Electrochemistry. *Chem.*  
37 *Soc. Rev.* **2010**, *39*, 3157–3180.
- 38 46 Osella, S.; Narita, A.; Schwab, M. G.; Hernandez, Y.; Feng, X. L.; Müllen, K.;  
39 Beljonne, D. Graphene Nanoribbons as Low Band Gap Donor Materials for  
40 Organic Photovoltaics: Quantum Chemical Aided Design. *ACS Nano* **2012**, *6*,  
41 *5539–5548*.
- 42 47 Jiao, L. Y.; Zhang, L.; Wang, X. R.; Diankov, G.; Dai, H. J. Narrow Graphene  
43 Nanoribbons from Carbon Nanotubes. *Nature* **2009**, *458*, 877–880.
- 44 48 Chmil, K.; Scherf, U. A Simple 2-Step Synthesis of a Novel, Fully Aromatic  
45 Ladder-Type Polymer. *Makromol. Chem. Rapid Commun.* **1993**, *14*, 217–222.
- 46 49 Narita, A.; Feng, X. L.; Hernandez, Y.; Jensen, S. A.; Bonn, M.; Yang, H.;  
47 Verzhbitskiy, I. A.; Casiraghi, C.; Hansen, M. R.; Koch, A. H. R.; *et al.* Synthesis  
48 of Structurally Well-Defined and Liquid-Phase-Processable Graphene  
49 Nanoribbons. *Nat. Chem.* **2014**, *6*, 126–132.
- 50 50 Abbas, A. N.; Liu, G.; Narita, A.; Orosco, M.; Feng, X. L.; Müllen, K.; Zhou, C. W.  
51 Deposition, Characterization, and Thin-Film-Based Chemical Sensing of Ultra-  
52 long Chemically Synthesized Graphene Nanoribbons. *J. Am. Chem. Soc.* **2014**,  
53 *136*, 7555–7558.
- 54  
55  
56  
57  
58  
59  
60

- 1  
2  
3 51 Lin, Y.-M.; Dimitrakopoulos, C.; Jenkins, K. A.; Farmer, D. B.; Chiu, H.-Y.; Grill,  
4 A.; Avouris, P. 100-GHz Transistors from Wafer-Scale Epitaxial Graphene.  
5 *Science* **2010**, *327*, 662–662.
- 6 52 Jensen, S. A.; Ulbricht, R.; Narita, A.; Feng, X. L.; Müllen, K.; Hertel, T.;  
7 Turchinovich, D.; Bonn, M. Ultrafast Photoconductivity of Graphene Nanoribbons  
8 and Carbon Nanotubes. *Nano Lett.* **2013**, *13*, 5925–5930.
- 9 53 Rader, H. J.; Rouhanipour, A.; Talarico, A. M.; Palermo, V.; Samori, P.; Müllen,  
10 K. Processing of Giant Graphene Molecules by Soft-Landing Mass Spectrometry.  
11 *Nat. Mater.* **2006**, *5*, 276–280.
- 12 54 Treier, M.; Pignedoli, C. A.; Laino, T.; Rieger, R.; Müllen, K.; Passerone, D.;  
13 Fasel, R. Surface-Assisted Cyclodehydrogenation Provides a Synthetic Route  
14 Towards Easily Processable and Chemically Tailored Nanographenes. *Nat.*  
15 *Chem.* **2011**, *3*, 61–67.
- 16 55 Lafferentz, L.; Eberhardt, V.; Dri, C.; Africh, C.; Comelli, G.; Esch, F.; Hecht, S.;  
17 Grill, L. Controlling On-Surface Polymerization by Hierarchical and Substrate-  
18 Directed Growth. *Nat. Chem.* **2012**, *4*, 215–220.
- 19 56 Chen, Y.-C.; de Oteyza, D. G.; Pedramrazi, Z.; Chen, C.; Fischer, F. R.;  
20 Crommie, M. F. Tuning the Band Gap of Graphene Nanoribbons Synthesized  
21 from Molecular Precursors. *ACS Nano*, **2013**, *7*, 6123–6128.
- 22 57 Cai, J. M.; Ruffieux, P.; Jaafar, R.; Bieri, M.; Braun, T.; Blankenburg, S.; Muoth,  
23 M.; Seitsonen, A. P.; Saleh, M.; Feng, X. L.; *et al.* Atomically Precise bottom-up  
24 Fabrication of Graphene Nanoribbons. *Nature* **2010**, *466*, 470–473.
- 25 58 Blankenburg, S.; Bieri, M.; Fasel, R.; Müllen, K.; Pignedoli, C. A.; Passerone, D.  
26 Porous Graphene as an Atmospheric Nanofilter. *Small* **2010**, *6*, 2266–2271.
- 27 59 Palma, C.-A.; Samori, P. Blueprinting Macromolecular Electronics. *Nat. Chem.*  
28 **2011**, *3*, 431–435.
- 29 60 Orgiu, E.; Samori, P. 25th Anniversary Article: Organic Electronics Marries  
30 Photochromism: Generation of Multifunctional Interfaces, Materials, and Devices.  
31 *Adv. Mater.* **2014**, *26*, 1827–1845.
- 32 61 Samori, P. Exploring Supramolecular Interactions and Architectures by Scanning  
33 Force Microscopies. *Chem. Soc. Rev.* **2005**, *34*, 551–561.
- 34 62 Blankenburg, S.; Cai, J. M.; Ruffieux, P.; Jaafar, R.; Passerone, D.; Feng, X. L.;  
35 Müllen, K.; Fasel, R.; Pignedoli, C. A. Intraribbon Heterojunction Formation in  
36 Ultranarrow Graphene Nanoribbons. *ACS Nano* **2012**, *6*, 2020–2025.
- 37 63 Talirz, L.; Söde, H.; Cai, J.; Ruffieux, P.; Blankenburg, S.; Jafaar, R.; Berger, R.;  
38 Feng, X. L.; Müllen, K.; Passerone, D.; *et al.* Termini of Bottom-Up Fabricated  
39 Graphene Nanoribbons, *J. Am. Chem. Soc.* **2013**, *135*, 2060–2063.
- 40 64 Zagranyski, Y.; Chen, L.; Jänsch, C.; Gessner, T.; Li, C.; Müllen, K. Toward  
41 Perylene Dyes by the Hundsdiecker Reaction. *Org. Lett.* **2014**, *16*, 2814–2817.

### Suggested Pull Quotes

Polyphenylene dendrimers create a unique functional nanoenvironment by way of a perfect covalent design.

It is a unique feature of our graphene nanoribbon fabrication, both in solution and on surfaces, that their geometric and electronic structures can be tuned by the nature of the monomeric building blocks.

1  
2  
3 Nanoscience must go beyond the catalogue of commercial compounds to make use  
4 of our collective chemical imagination.  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60