

VARYING TREATMENTS ON THE ACTIVATION OF VPO

Ayub, Ibrar¹; Su, Dangsheng¹; Kharlamov, Alexey²; Schlögl, Robert¹

1. Fritz-Haber Institute of the Max Planck Society, Faradayweg 4-6, D-14195 Berlin, Germany

2. Institute for Problems of Materials Science, Kiev, Ukraine
Fax : +49 (0)30 8413 4405 E-mail : ayub@fhi-berlin.mpg.de

Mechanical treatment of VPO catalyst causes a substantial increase of both catalytic activity in *n*-butane oxidation and the selectivity to maleic anhydride [1]. Changes in specific surface area and anisotropic deformation take place. Mechanochemical treatment of the initial reagent impairs such properties that they remarkably influence the catalytic properties of the final catalyst.

VOHPO₄·0.5H₂O (VHP) was mechanotreated in ethanol and air for a duration of time and the morphology studied under scanning and transmission electron microscopes (SEM, TEM) and by x-ray powder diffraction (XRD). This was compared with the morphology of the initial reagent and sample thermally treated in a vacuum. Also the product (VO)₂P₂O₇ (VPP), which was obtained from VOHPO₄·0.5H₂O in reactor under butane/air gas mixture, was compared. SEM shows that the initial sample mainly of flat smooth needle like particles, which are held together like a blossom morphology. Under mechanochemical treatment the blossom morphology is lost and layer formation forms, with more circular particles. XRD shows that milling in ethanol for 5 minutes broadened the peaks, indicating smaller particle size but did not change the phase. Milling in air for 28 minutes gave an amorphous phase also supported by the electron diffraction pattern which shows a diffused ring pattern. Milling for longer converted VHP to VPP. The thermally activated sample shows a phase change to (VO)₂P₂O₇ but minor phase of the initial material is still present.

Keywords: VPO, mechanochemical treatment, electron microscopy

Acknowledgements: The work at FHI is supported by SFB 546. I.A. thanks MPG for the scholarship.

[1] V.A. Zazhigalov, J. Haber, J. Stoch, A.I. Kharlamov, L.V. Bogutskaya, I.V. Bacherikova, and A. Kowal, *Solid State Ionics*, **101-103** (1997), 1257.